


PC-LN2-16.6 DETECTOR SERIES PRELIMINARY DATASHEET

**HgCdTe photoconductive
infrared detectors optimized
for operation at 77 K**



VFP Dewar KR163 Dewar KR323

FEATURES

- Spectral range: over 18.0 μm
- Large active area
- Front-side illuminated
- Active element material optimized for operation at 77 K
- VFP is a specially designed flatpack package (without a window) optimized for easy self-assembly in LN2 metal dewars
- Possible assembly of a temperature sensor
- Active area dimension 0.25 mm $\times$ 0.25 mm available (on request)
- Other acceptance angle values available (on request)

APPLICATIONS

- FTIR spectroscopy


SERIES CONFIGURATION

Detector symbol	Cooling	Temperature sensor	Active area, A, mm×mm	Optical immersion	Package	Acceptance angle, Φ, deg.	Window
PC-LN2-16.6-1x1-VFP-NW-50	LN2 (for operation in 77 K)	no	1x1	no	VFP (flatpack)	~50	no
PC-LN2-16.6-1x1-VFP-KR163-wZnSeAR-50	LN2 T _{chip} ≅77K				VFP-KR163	~50	wZnSeAR (3 deg. wedged zinc selenide, anti-reflection coating)
PC-LN2-16.6-1x1-VFP-KR323-wZnSeAR-36					VFP-KR323	~36	

SPECIFICATION ($T_{\text{amb}} = 293\text{ K}$, $T_{\text{chip}} = 77\text{ K}$, $I_b = 15\text{ mA}$)

Detector symbol	Peak wavelength	Cut-off wavelength (10%)	Detectivity	Voltage responsivity	Resistance	Bias current
	λ_{peak}	$\lambda_{\text{cut-off}}$	$D^*(\lambda_{\text{peak}}, 20\text{kHz})$	$R_v(\lambda_{\text{peak}})$	R	I_b
	μm	μm	$\text{cm}\cdot\text{Hz}^{1/2}/\text{W}$	V/W	Ω	mA
	Typ.	Typ.	Typ.	Typ.	Typ.	Typ.
PC-LN2-16.6-1x1-VFP-NW-50	14.3	18.1	1.5×10^{10}	500	40	15
PC-LN2-16.6-1x1-VFP-KR163-wZnSeAR-50						
PC-LN2-16.6-1x1-VFP-KR323-wZnSeAR-36						

SPECTRAL RESPONSE (Typ., $T_{amb} = 293\text{ K}$, $T_{chip} = 77\text{ K}$, $I_b = 15\text{ mA}$)



MECHANICAL LAYOUT AND SIGNAL OUTPUT

- [LN2-VFP\(2p\), PC detector technical drawing](#)
- [Dewar KR163 technical drawing](#)
- [Dewar KR323 technical drawing](#)

ABSOLUTE MAXIMUM RATINGS

Parameter	Test conditions, remarks	Value	Unit
Ambient operating temperature, T_{amb}	Operation at $T_{amb} > 30^{\circ}\text{C}$ may increase the liquid nitrogen consumption in the dewar	-20 to 30	$^{\circ}\text{C}$
Storage temperature, T_{stg}		-20 to 50	$^{\circ}\text{C}$
Storage humidity	No dew condensation	10 to 90	%
Maximum incident optical power density	Continuous wave (CW) or single pulses $> 1\text{ }\mu\text{s}$ duration	100	W/cm^2
	Single pulses $< 1\text{ }\mu\text{s}$ duration	1	MW/cm^2
Maximum bias current, $I_{b\text{ max}}$		25	mA

Stresses beyond those listed under absolute maximum ratings may cause permanent damage to the device. Constant or repeated exposure to absolute maximum rating conditions may affect the quality and reliability of the device.